

MatTOP

C 2A95

Clear coat, silk mat

Application:	Advance Series - Clear coat especially for ONYX HD basecoat.
Key Features:	Silk mat clear coat for special OEM finishes.
Remarks:	Mix with MatTOP+ C 2A93 clear coat in order to achieve desired gloss level. Stir well before use. MatTOP C 2A95 must not be used in mixing shelves.

Density	0.9-1.1 g/cm ³
Storage temperature	5-45 °C
Shelf life	24 months

2:1



Mixing Ratio

100 % by volume

C 2A95 Clear coat, silk mat



Hardener

50 % by volume

H 2A94 Hardener, mat



Spray viscosity at 20°C DIN 4: 18-21 s

ISO 4: 40-55 s

Potlife at 20°C

2 h

Safety advice:

2004/42/IIIB(e)(840)629: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 grams of VOC per liter. The VOC content of this product is 629 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

MatTOP

C 2A95

Clear coat, silk mat



HVLP spray gun



Compliant gravity-feed spray gun

Application pressure	2 bar	2 bar
Nozzle pressure	0.7 bar	
Nozzle size	1.3-1.5	1.3-1.4
Number of spray coats	2	

Flash off at 20°C Flash off until mat between spray coats and before stoving. After the first spray coat, allow to flash off for 10 - 15 min, after the second spray coat for 15 - 20 min.
Do not flash off for more than 25 minutes after each spray coat.

Film thickness 40-50 µm

Drying



Drying at 20°C 8 h

Drying at 60°C 30 min



Infrared (short wave) 9 min
3 min at 50% + 6 min at 100%

Remark With mat surfaces it is not possible to remove dust inclusions by polishing because polishing changes the gloss level. Therefore, it is very important to work very carefully during cleaning and application.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/II B(e)(840)629: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 grams of VOC per liter. The VOC content of this product is 629 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.