

# SUPREMETOP CP II

C 2486

HS clear ultra scratch resistant

- Application:** Low-solvent clear for repairing vehicles with scratch-resistant original paint finishes. SUPREMETOP CP II was designed for use on ONYX HD and DIAMONT basecoats (add 3% of H 9000 to DIAMONT mixing bases).
- Key Features:** The SUPREMETOP CP II clearcoat ensures an excellent and perfect finish quality. The product is scratch-resistant thanks to its good "reflow" properties. SUPREMETOP CP II offers excellent polishability.
- Remarks:** Note: Use slower R 2300 thinner for higher temperatures or when refinishing large surfaces. For combi-booths, take additional heating rate into account until panel temperature has been reached.

---

<b>Solid Content</b>	60 % +/- 2
<b>Density</b>	0.96-1.06 g/cm <sup>3</sup>
<b>Storage temperature</b>	5-45 °C
<b>Shelf life</b>	36 months

---

**Safety advice:**

**2004/42/IIIB(d)420)419:** The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# SUPREMETOP CP II

**C 2486**

**HS clear ultra scratch resistant**

**3:1:1**



**Mixing Ratio**

100 Parts by volume C 2486 HS clear ultra scratch resistant



**Hardener**

33 Parts by volume H 2500 Hardener, medium



**Thinner**

33 Parts by volume R 2200 Thinner, medium



**Spray viscosity at 20°C**

DIN 4: 21-23 s

**Potlife at 20°C**

1 h

		 <b>HVLV spray gun</b>	 <b>Compliant gravity-feed spray gun</b>
<b>Application pressure</b>	<b>bar</b>		2
<b>Nozzle pressure</b>	<b>bar</b>	0.7	
<b>Nozzle size</b>		1.3	1.3-1.4
<b>Number of spray coats</b>			2
<b>Flash off at 20°C</b>	<b>min</b>		3-5 between spraycoats
<b>Film thickness</b>	<b>µm</b>		40-60

**Safety advice:**

**2004/42/IIIB(d)420)419:** The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# SUPREMETOP CP II

C 2486

HS clear ultra scratch resistant

## Drying



Drying at 60°C 40 min



Infrared (short wave) 10 min

**Remark** Finishing operations after specified drying times and cooling.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

### Safety advice:

**2004/42/IIIB(d)420)419:** The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

