

UV Fill-R Grey

PM 2P93

UV primer filler, grey

Application:	Pioneer Series - undercoat solutions.
Key Features:	Eco effectiveness aerosol can - UV primer filler. For good corrosion resistance, excellent topcoat holdout.
Remarks:	The material is ready for use. Product is suitable on <ul style="list-style-type: none">• Sheet steel• Galvanised sheet steel• Aluminium• Old paintwork• GRP / SMC

Storage temperature	5-45 °C
Shelf life	12 months



Cleaning

Clean with PK 1P10 or PK 2P10.

Safety advice:

2004/42/IIIB(e)(840)655: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 grams of VOC per liter. The VOC content of this product is 655 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



UV Fill-R Grey

PM 2P93

UV primer filler, grey

Handling



Do not use deformed aerosol cans. While shaking the can, do not strike against solid objects. During shaking, the mixing balls are released. Avoid bumps, friction and impact.



Shake vigorously for 2 min. before each use.
Do not apply in direct sunlight.



Number of spray coats: $\frac{1}{2} + 1$

Film thickness: max. 80 μm

Flash off at 20°C: 20 s between the first and the second coat.

Remark: Alternatively max. 120 μm with 60 s between the first and the second coat and 90 s flash off before UV drying.

Drying



UV Curing

5 min (UV-A > 6 mW/ cm²)



Orbital sanding, dry

P400 - P600

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIIB(e)(840)655: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 grams of VOC per liter. The VOC content of this product is 655 g/l.

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.